

# PRODUCT DATA SHEET

## Sikagard<sup>®</sup>-62

### 2-PART EPOXY PROTECTIVE COATING / LINING SYSTEM

#### DESCRIPTION

Sikagard<sup>®</sup>-62 is a two part, rigid, 100 % solids, coloured high build epoxy resin based protective coating with high resistance to abrasion and chemical attack.

#### USES

Sikagard<sup>®</sup>-62 may only be used by experienced professionals.

- Chemical resistant protective layer on concrete, stone, cementitious mortars and renderings, epoxy cement, epoxy resin based products and steel
- Lining in storage tanks and silos
- Anti-corrosion for chemical bunded areas, food and beverage processing plants, sewage works, water retaining structures, chemical and pharmaceutical facilities.

#### FEATURES

- Solvent free
- Good mechanical and chemical resistance
- High build
- Impervious to liquids
- Easy to mix and to apply

#### PRODUCT INFORMATION

<b>Composition</b>	Epoxy resin	
<b>Packaging</b>	Part A	8.4 kg
	Part B	3.0 kg
	Sikafloor Pigment x 1	1.15kg
	Total kit 12.55kg - 9.2 L	Total kit 12.55kg - 9.2 L
<b>Shelf life</b>	Part A: 24 months Part B: 24 months From date of production if stored properly.	

#### SUSTAINABILITY

Conformity with LEED v2009 IEQc 4.2: Low-Emitting Materials - Paints and Coatings

#### CERTIFICATES AND TEST REPORTS

- Potable Water approved to AS/NZS 4020:2018 - Testing of products for use in contact with drinking water
- Coating for concrete protection according the requirements of EN 1504-2:2004, Declaration of Performance 0206060100100000011008, certified by FPC Notified Body and provided with CE marking
- WRAS, test report No. M104991, 2011, Contact with water for wholesome purposes according BS 6920-1:2000

<b>Storage conditions</b>	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C. Protected from direct sunlight.
<b>Appearance and colour</b>	RAL colour range - refer to Sika colour chart
<b>Density</b>	Mixed resin ~1.37 kg/l Density values determined at +23 °C

## TECHNICAL INFORMATION

<b>Shore D Hardness</b>	~80	(DIN 5305)												
<b>Mechanical resistance</b>	<table border="1"> <tr> <td>Taber Abraser</td> <td>CS 10/ 1000/ 1000</td> <td>24.4mg</td> <td>(ASTM D 4060)</td> </tr> <tr> <td>Taber Abraser</td> <td>CS 17/ 1000/ 1000</td> <td>70 mg</td> <td></td> </tr> <tr> <td>Taber Abraser</td> <td>H 22/ 1000/ 1000</td> <td>560.6mg</td> <td></td> </tr> </table>	Taber Abraser	CS 10/ 1000/ 1000	24.4mg	(ASTM D 4060)	Taber Abraser	CS 17/ 1000/ 1000	70 mg		Taber Abraser	H 22/ 1000/ 1000	560.6mg		
Taber Abraser	CS 10/ 1000/ 1000	24.4mg	(ASTM D 4060)											
Taber Abraser	CS 17/ 1000/ 1000	70 mg												
Taber Abraser	H 22/ 1000/ 1000	560.6mg												
<b>Tensile adhesion strength</b>	> 1.5 N/mm <sup>2</sup> to concrete	(ISO 4624)												
<b>Temperature resistance</b>	<table border="1"> <thead> <tr> <th>Exposure</th> <th>Dry heat</th> </tr> </thead> <tbody> <tr> <td>Permanent</td> <td>+50 °C</td> </tr> <tr> <td>max. 7 days</td> <td>+80 °C</td> </tr> <tr> <td>max. 12 hours</td> <td>+100 °C</td> </tr> </tbody> </table>	Exposure	Dry heat	Permanent	+50 °C	max. 7 days	+80 °C	max. 12 hours	+100 °C					
Exposure	Dry heat													
Permanent	+50 °C													
max. 7 days	+80 °C													
max. 12 hours	+100 °C													
<b>Chemical resistance</b>	Please contact Sika technical service for specific information.													

## SYSTEM INFORMATION

<b>Systems</b>	<p><b>Standard Three Coat System: (DFT from 600um - 800um)</b>  <i>Primer:</i> Sikafloor 160 or 161 + <i>1st Coat:</i> Sikagard 62 + <i>2nd Coat:</i> Sikagard 62</p> <p><b>Fibreglass Laminate System: (DFT from 1000um - 1200um) Subject to glass Thickness</b>  <i>Primer:</i> Sikafloor 160, Fibreglass, Sikafloor 160 + <i>1st Coat:</i> Sikagard 62 + <i>2nd Coat:</i> Sikagard 62</p> <p><b>SikaGard EpoCem 720 System: (DFT from 1200um +) Subject to EpoCem 720 Thickness</b>  <b>Typically used on High Wear, Damaged or High moisture content substrate applications:</b>  SikaGard EpoCem 720 + <i>1st Coat:</i> Sikagard 62 + <i>2nd Coat:</i> Sikagard 62  Please refer to Sikagard 720 EpoCem PDS  Please refer to individual Product Data Sheets and consult the Sika Technical Department for specific Consumption Priming and Coverage Information pertaining to project requirements.</p>
----------------	--

## APPLICATION INFORMATION

<b>Mixing ratio</b>	Part A : Part B = 3 : 1 by weight      2.1 : 1 by volume
<b>Consumption</b>	~0.25 - 0.35 L m <sup>2</sup> per layer depending on system structure requirements
<b>Layer thickness</b>	~0.2 - 0.3 mm per layer depending on substrate condition, method application and temperature. Recommended number of coats - minimum 2 and possibly 3 depending on required film build for the given environment.
<b>Ambient air temperature</b>	+8 °C min. / +40 °C max.
<b>Relative air humidity</b>	< 80 %
<b>Substrate temperature</b>	+8 °C min. / +40 °C max. Minimum 3 °C above dew point, beware of condensation

Pot Life	Temperature		Time	
	+10 °C			~30 min
	+20 °C			~20 min
	+30 °C			~10 min

---

Waiting time to overcoating	Temperature		Min.	Max.	Full cure
	+10 °C		~ 30 hours	~ 3 days	~ 14 days
	+20 °C		~ 10 hours	~ 2 days	~ 10days
	+30 °C		~ 6 hours	~ 1 day	~ 5 days

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

- Do not apply Sikagard®-62 on moist substrates
- Sag resistance on vertical surface is approx. 200 µm.
- Freshly applied Sikagard®-62 must be protected from damp, condensation and water for at least 24 hours
- For exact colour matching ensure using material from the same control batch numbers.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

The substrate must be sound, clean, dry, free from contaminants such as dirt, grease, oil, old coatings, release agents, laitance and other adhesion preventing or influencing substances.

On high absorbent, non-sound or non cement based substrates precautions have to be taken and a suitable primer has to be used.

### SUBSTRATE PREPARATION

#### Concrete Substrate

Concrete substrate must be prepared mechanically to achieve an open textured surface.

Weak areas in the substrate must be removed and surface defects such as blowholes and voids must be fully exposed.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Open voids and blowholes need to be closed with a suitable Sika® pore filling mortar. The roughness of the substrate needs to be levelled with a suitable Sika® rendering and levelling mortar.

### Steel Surface

Steel surface must be prepared mechanically using abrasive blast cleaning. The level SSPC-SP 10 "near white metal blast cleaned" or level Sa 2 ½ according to ISO EN 12944-4 has to be achieved. Welds and joints have to be prepared according to EN 14879, part 1. After blast cleaning remove all dust dirt and blasting material. In order to maintain the surface conditions after blast cleaning air-conditioning is recommended.

### MIXING

Prior to mixing stir Part A mechanically then add required pigment and stir for a further 1 minute, Add all Part B to Part A and mix for a further 3 minutes until a uniform mix has been achieved. Use a low speed electrical stirrer (300–400 rpm) to avoid air entrapment. To ensure proper mixing pour material into a clean container and stir again.

### APPLICATION

Apply by brush, roller or airless spray.

### CLEANING OF EQUIPMENT

Clean all tools with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Australia Pty Limited**

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

**Product Data Sheet**

Sikagard®-62

July 2023, Version 04.04

020303120020000027

